

## AUAV00111 Dulux Avista Resurfacing Accelerator

### Introduction

Product Line  
**FD578085-4L**

### Product Overview and Image

Accelerator for speeding up drying time in cooler temperatures in Dulux Avista Resurfacing system.



### Features and Benefits

- Speeding up set times in cooler temperatures

### Uses

Used in Dulux Avista resurfacing systems

### Typical Properties

Drying Time

Min

Max

Recommended

Comments

**Coverage: Maximum accelerator ratios will cover 8 bags, minimum 11 bag**

Typical Property Notes

Specific gravity: 1.33 g/cm<sup>2</sup>

### Product Properties

Conditions

**32% w/w Calcium Chloride solution**

**Application Guide**

Application Procedure and Equipment

Dulux® Avista® Resurfacing Accelerator is recommended to be used when the temperature is below 15°C but above 10°C during the application of Dulux Avista Resurfacing Compound as it will speed up the drying time.

HOW TO USE

1. Add 350 to 500 ml of Dulux Avista Resurfacing Accelerator to a clean bucket.
2. Add 3.25 to 3.5 litres of clean water to the bucket.
3. Add Dulux Avista Resurfacing Colour Oxide and mix thoroughly with a mechanical mixer at low speed until mix colour is uniform.
4. Slowly add the Dulux Avista Base Compound and mix thoroughly for 3 mins after the complete bag has been added.
5. Follow application instructions for Dulux Avista Resurfacing Compound as detailed on the product Technical Data Sheet (TDS) at [www.duluxavista.com.au](http://www.duluxavista.com.au)

**Health and Safety**

SDS Number  
**PAR009631**

SDS Link  
[View SDS Link](#)

**Please refer to SDS Link. In case of emergency, please call 1800 220 770.**

**Precautions and Limitations**

- Do not exceed 500ml and keep water ratios to the minimum.
- To be used when the temperature is above 10°C but below 15°C during the application of the Dulux Avista Resurfacing Base Compound
- Store in cool, dry area in unopened container.

**Disclaimer**

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from [www.duspecplus.com.au](http://www.duspecplus.com.au). Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.