







AUAV00006 Dulux Avista Resurfacing Base Compound

Introduction	
Part A Resurfacing Base Compound	Part B Colour Oxide
Product Code FD500998-20KG	

Product Overview and Image	
<p>Dulux Avista Resurfacing Base Compound is a decorative concrete coating suitable for application over existing cured concrete surfaces. It can be tinted to a range of colours by adding Dulux Avista Colour Oxide.</p>	
<p>Product Category Concrete Resurfacing</p>	

Features and Benefits
<ul style="list-style-type: none"> • Excellent adhesion to most concrete surfaces • Spray or trowel application • Wide range of colours • Variety of finishes available • Convenient water clean up • Upto P5 slip rating • Highly durable

Uses
<p>Dulux Avista Resurfacing is suitable for use on driveways, patios, pool surrounds, domestic and commercial pavements and certain road applications. The concrete being resurfaced must be structurally sound and at least 28 days old.</p>

Typical Properties			
Components 3			
Shelf Life Inspect bag after 2 years. Ensure bag is stored in a cool, dry location.		Pot Life approx. 30 minutes, depending on ambient conditions	
Yield 12.5L		V.O.C. Content 11 grams per litre	
Clean Up  Water			
Sizes 20KG			
Application Methods  Floor Squeegee  Broom  Trowel  Hopper Gun			
Specifications			
	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	<input type="text" value="15"/>	<input type="text" value="30"/>	<input type="text"/>
Drying Time			
	Min	Max	Recommended
Touch Dry (min)	<input type="text" value="30"/>	<input type="text" value="60"/>	<input type="text"/>
Recoat Time (min/hours)	<input type="text" value="40"/>	<input type="text" value="NA"/>	<input type="text"/>
Comments	Dulux Avista Concrete Resurfacing can be recoated as soon as the surface can be walked on. Drying/recoat times will vary depending on ambient conditions.		

Product Properties	
Conditions Chemical properties will vary depending on clear topcoat used. Refer to relevant sealer TDS.	
Compressive Strength (AS1478.2-2005) 10MPa@1 day, 30MPa @ 7 days, 40MPa @ 28 days	
Modulus of Rupture (Flexural Strength) (AS1012.11-2000) 5MPa@1 day, 7MPa@7 days, 10MPa@ 28 days	Indirect Tensile Strength (AS1012.10-2000) 1MPa@ 1 day, 3MPa@ 7 days, 5MPa@ 28 days
Taber Abrasion Index (CS10 Wheel, 1kg load, 1000 cycles) <100	

Slip Rating			
Surface Finish	Finish Coat	Slip Reducing Additive	Result
Resurfacing Trowel finished	Dulux Avista General Purpose Sealer Semi-Gloss	No	P1
Resurfacing Spray finished	Dulux Avista General Purpose Sealer Semi-Gloss	No	P5

Maintenances
<p>Surface should be cleaned regularly, removing mud, dirt & gravel by sweeping and/or pressure cleaning.</p> <p>Remove oil, grease and other chemicals contaminants immediately.</p> <p>Remove excess leaf & organic matter to avoid staining.</p> <p>Avoid driving on surface with rocks in tyres.</p> <p>Recoat with Dulux Avista General Purpose or Extended Wear Sealer approximately every 2 years. *</p> <p>*Actual lifespan of the sealer may vary depending on frequency of use & environmental factors.</p>

Application Guide
<p>Surface Preparation</p> <p>Preparation of the area is extremely important to ensure good adhesion. Failure to properly prepare the surface can result in failure of the Dulux Avista Concrete Resurfacing System.</p> <p>Ensure concrete is sufficiently cured (recommended minimum 14 days) & structurally sound. Any previous coatings must be removed by grinding, stripping or sand blasting.</p> <p>If surface contains non structural cracks, grind out and filling should be undertaken with Dulux Avista Crack Repair Kit. Additional saw cuts may be required to help reduce stress on the slab & minimise the chances of future cracks appearing. Future movement in the concrete may cause cracks to appear that may affect adhesion and could result in chipping of the resurfaced coating.</p> <p>Concrete is to be clean and free of grease, oil, paint or any curing agent. Stiff broom and general purpose cleaner recommended. Any oil stains should be treated & cleaned with an industrial degreaser. Pressure clean surface at a minimum of 3000 PSI.</p> <p>Acid etch with hydrochloric acid. Dilute approx 20 parts water to 1 part acid (depending on porosity) to remove any loosely bound cement and laitance.</p> <p>Note: smooth concrete will require a higher acid content. Maximum strength - 10 parts water to 1 part acid.</p> <p>Pressure clean immediately at minimum 3000psi to clean and remove all remnants of acid (do not allow acid to dry on surface).</p> <p>Masking and taping</p> <p>Ensure all surfaces surrounding the area to be sprayed, including grass and plants, should be covered or masked and taped.</p> <p>Expansion joints cannot be filled with resurfacing compound. Joints should be taped or filled with rubber or foam and removed before final spray.</p> <p>Priming</p> <p>The area is primed with Dulux Avista Resurfacing Primer. 1 part Resurfacing Primer: 3 parts water by volume.</p> <p>Apply evenly on a damp surface by broom, roller or sprayer. Do not allow primer to pool. Allowing primer to dry in a pooling area can affect adhesion. The first coat of Dulux Avista Resurfacing compound should be applied while the primer is still wet.</p>

<p>Application Procedure and Equipment</p> <p>Add required amount of clean potable water (3.6 - 4.0 L) in a clean 20L bucket and add Avista Resurfacing Colour Oxide and mix thoroughly with mechanical mixer at low speed until mix colour is uniform.</p> <p>Slowly add Dulux Avista Resurfacing Base Compound, mixing continually.</p> <p>Once full content has been added, mix for a further 3 minutes. This step is critical in activating the polymers to achieve an even consistent mixture.</p> <p>First coat should always be applied to a damp, primed surfaces. Applicable to all trowel or squeegee application methods.</p> <p>Squeegee/Trowel application (recommended for first coat)</p> <p>Pour a manageable quantity of Dulux Avista mixture onto the damp, primed concrete surface. Use squeegee or trowel evenly spread the resurfacing compound over the surface.</p> <p>Do not exceed a thickness of 4 mm per coat, as this may lead to shrinkage cracking.</p> <p>Subsequent trowel or spray coats can be applied to achieve desired decorative finish.</p> <p>Spray application</p> <p>Application will require a moisture trap air compressor & hopper gun. Recommended minimum compressor specs: 12 cfm with a 70L tank.</p> <p>Add mix to hopper, ensuring not to overfill - recommend half full.</p> <p>Before applying to surface, spray on separate fibro test board to obtain desired texture. Adjust pressure to vary texture.</p> <p>Spray evenly across the surface, holding the hopper approximately 600mm from the ground.</p> <p>Once area has been completely covered, allow to dry sufficiently to walk on.</p> <p>Minimum 2 coats at total of minimum 3mm thickness required to achieve sufficient wear factor.</p> <p>The Dulux Avista Resurfacing System must be sealed once the surface is completely dry. Options for sealing include:</p> <ul style="list-style-type: none"> - Dulux Avista General Purpose Sealer (S/G or matt) - Dulux Avista Extended Wear Sealer

- Dulux Avista 2 Pack Urethane
- Dulux Avista Polyaspartic Sealer

Health and Safety

SDS Number	SDS Link View SDS Link
Please refer to SDS Link. In case of emergency, please call 1800 220 770.	

Precautions and Limitations

Do not apply in temperatures below 10°C as curing time is significantly delayed. It is not advisable to apply onto very hot surfaces (greater than 40°C) as this can affect cure. Under very hot conditions shading the area may be required.

Dulux Avista Resurfacing System is a decorative coating only. Cracks in the concrete base may reflect through & future movement in the concrete substrate may also result in cracking in the resurfacing system.

After sealing it is recommended that the sealed surface be protected from:

- Rain/water/sprinkler systems for minimum 6 hours
- Foot traffic for a minimum of 24 hours
- Vehicle traffic for a minimum of 5 days

Actual time frame may vary depending on weather conditions and coating thickness. Check suitability before allowing traffic.

Transport and Storage

Line Shade /Pack A	
Resurfacing Base Compound	
Size:	Weight:
<input type="text" value="20kg"/>	<input type="text" value="20.82kg"/>
Pack B	
Color Oxide	
Size:	Weight:
<input type="text" value="1kg"/>	<input type="text" value="1kg"/>

Disclaimer

This Data Sheet is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Data Sheet does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Data Sheet is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Data Sheet, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Data Sheet, and as recommended on the applicable Safety Data Sheets for the relevant products, available from www.duspecplus.com.au. Climatic conditions at application time can affect product suitability and performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Data Sheet cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS 4361 Parts 1 and 2 and Worksafe Australia guidelines.